

1. Identification of the substance/mixture and of the company/undertaking

Manufacturer: Axalta Coating Systems, LLC
Applied Corporate Center
50 Applied Card Way, Suite 300
Glen Mills, PA 19342

Telephone: Product information: (855) 6-AXALTA
Medical emergency: (855) 274-5698
Transportation emergency: (800) 424-9300 (CHEMTREC)

Product: **Imron® Elite™ Related Products and Axalta™ Excel™**

DOT Shipping Name: See DOT Addendum.

Hazardous Materials Information: See Section 10.

Copyright 2014, Axalta Coating Systems, LLC and all affiliates. All rights reserved. Copies may be made only for those using Axalta Coating Systems products.

2. Composition/information on ingredients

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
1,2,4-trimethyl benzene	95-63-6	7.0@44.4 °C	A 25.0 ppm, O 25.0 ppm
1,3,5-trimethyl benzene	108-67-8	None	A 25.0 ppm, O None
1,6-hexamethylene diisocyanate	822-06-0	0.0@25.0 °C	A 5.0 ppb, O None
2,4-pentanedione	123-54-6	9.0	A 25.0 ppm Skin, D 5.0 ppm 8 & 12 hour TWA, O None
2-ethylhexyl acetate	103-09-3	0.5	A None, O None
2-methyl butyl acetate	624-41-9	None	A 100.0 ppm 15 min STEL, A 50.0 ppm, O None
4,6-dimethyl-2-heptanone	19549-80-5	None	A None, O None
4-chlorobenzotrifluoride	98-56-6	7.6@25.0 °C	D 20.0 ppm 8 & 12 hour TWA, A None, O None
Acetic acid	64-19-7	15.4	A 15.0 ppm 15 min STEL, A 10.0 ppm, O 10.0 ppm, D 10.0 ppm 8 & 12 hour TWA
Acetone	67-64-1	247.0@68.0 °F	A 750.0 ppm 15 min STEL, A 500.0 ppm, O 1000.0 ppm, D 500.0 ppm 8 & 12 hour TWA
Acrylic polymer-A	Not Avail	None	A None, O None
Acrylic polymer-B	104032-39-5	None	A None, O None
Acrylic polymer-C	32458-06-3	None	A None, O None
Acrylic resin	Not Avail	None	A None, O None
Additive	Not Avail	None	A None, O None
Aliphatic polyisocyanate resin	28182-81-2	<0.0	S 0.5 mg/m3, A None, O None
Aluminum	7429-90-5	None	O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, D 0.5 mg/m3 8 & 12 hour TWA, A None
Aluminum hydroxide	21645-51-2	None	A 1.0 mg/m3, O None
Aluminum salt	Not Avail	None	A None, O None
Amorphous silica-A	7631-86-9	None	A 3.0 mg/m3 Respirable Dust, O 20.0 mppcf, D 3.0 mg/m3, D 6.0 mg/m3
Amorphous silica-B	92797-60-9	None	A 2.0 mg/m3 Respirable Dust, O 1.0 mg/m3 15 min STEL, D 1.0 mg/m3
Amorphous silica - silica base	63231-67-4	None	D 2.0 mg/m3 Respirable Dust, D 2.0 mg/kg 12 hr TWA, A None, O None
Aromatic hydrocarbon-A	64742-94-5	10.0	D 100.0 ppm 8 & 12 hour TWA, A None, O None
Aromatic hydrocarbon-B	64742-95-6	10.0@25.0 °C	D 50.0 ppm 8 & 12 hour TWA, A None, O None
Barium sulfate	7727-43-7	None	O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, D 10.0 mg/m3 8 & 12 hour TWA Total Dust, D 5.0 mg/m3 8 & 12 hour TWA Respirable Dust, A None
Bis(1,2,2,6,6-pentamethyl-4-piperidiny) sebacate	41556-26-7	None	A None, O None
Bismuth vanadium oxide	14059-33-7	None	A None, O None
Butanedioic acid, dimethyl ester	106-65-0	None	D 10.0 mg/m3, A None, O None
Butyl acetate	123-86-4	15.0	A 200.0 ppm 15 min STEL, A 150.0 ppm, O 150.0 ppm
C.i. pigment blue 60	81-77-6	None	A None, O None
C.i. pigment red 254	84632-65-5	None	A None, O None
C.i. pigment yellow 154	68134-22-5	None	A None, O None
Calcium sodium borosilicate	65997-17-3	None	A 10.0 mg/m3 inhalable dust, O 15.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, D 5.0 mg/m3 8 & 12 hour TWA non fibrous particulate
Carbazole violet pigment	6358-30-1	None	A None, O None
Carbon black	1333-86-4	None	A 3.0 mg/m3, O 3.5 mg/m3, D 0.5 mg/m3 8 & 12 hour TWA

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Cumene	98-82-8	3.7	A 50.0 ppm, O 50.0 ppm Skin
Decanedioic acid, methyl 1,2,2,6,6-pentamethyl-4-piperidinyl ester	82919-37-7	None	A None, O None
Dibutyl tin dilaurate	77-58-7	<10.0	A 0.2 mg/m ³ 15 min STEL Sn, A 0.1 mg/m ³ Sn, O 0.1 mg/m ³ Sn
Diisobutyl ketone	108-83-8	1.8	A 25.0 ppm, O 50.0 ppm
Dimethyl glutarate	1119-40-0	0.2	D 10.0 mg/m ³ 8 & 12 hour TWA, A None, O None
Ethyl 3-ethoxy propionate	763-69-9	2.3	A None, O None
Ethyl acetate	141-78-6	100.0	A 400.0 ppm, O 400.0 ppm
Ethylbenzene	100-41-4	9.5	A 20.0 ppm, O 100.0 ppm, D 25.0 ppm 8 & 12 hour TWA
Ethylene glycol monobutyl ether	111-76-2	0.6	A 20.0 ppm, O 50.0 ppm Skin, D 20.0 ppm 8 & 12 hour TWA
Ethylene glycol monobutyl ether acetate	112-07-2	0.3	A 20.0 ppm, D 20.0 ppm 8 & 12 hour TWA, O None
Heavy mineral spirits	64741-65-7	10.0@25.0 °C	D 100.0 ppm, A None, O None
Heptane	142-82-5	45.0@66.0 °F	A 500.0 ppm 15 min STEL, A 400.0 ppm, O 500.0 ppm
Hexanedioic acid, dimethyl ester	627-93-0	None	D 10.0 mg/m ³ 8 & 12 hour TWA, A None, O None
Hydrotreated heavy naphtha (petroleum)-A	64742-47-8	3.3@68.0 °F	A None, O None
Hydrotreated heavy naphtha (petroleum)-B	64742-48-9	0.7@68.0 °F	A 100.0 ppm, O 500.0 ppm, D 100.0 ppm
Iron hydroxide	20344-49-4	None	A None, O None
Iron oxide	1309-37-1	None	A 5.0 mg/m ³ Respirable Dust, O 10.0 mg/m ³ , D 3.0 mg/m ³
Isoindolinone pigment	36888-99-0	None	A None, O None
Isopropyl alcohol	67-63-0	60.2	A None, O None
Kaolin	1332-58-7	None	A 2.0 mg/m ³ Respirable Dust, O 15.0 mg/m ³ TWA Total Dust, O 5.0 mg/m ³ TWA Respirable Dust
Kerosine (petroleum), hydrodesulfurized	64742-81-0	10.0	A None, O None
Light yellow lemon yellow oxide pigment	51274-00-1	None	A None, O None
Limestone (calcium carbonate)	1317-65-3	None	A 10.0 mg/m ³ , O 15.0 mg/m ³ Total Dust, O 5.0 mg/m ³ Respirable Dust
Methyl acetate	79-20-9	179.5@68.0 °F	A 250.0 ppm 15 min STEL, A 200.0 ppm, O 200.0 ppm
Methyl amyl ketone	110-43-0	3.4	A 50.0 ppm, O 100.0 ppm
Methyl ethyl ketone	78-93-3	71.2	A 300.0 ppm 15 min STEL, A 200.0 ppm, O 200.0 ppm, D 300.0 ppm 15 min TWA, D 200.0 ppm 8 & 12 hour TWA
Methyl isoamyl ketone	110-12-3	5.3	A 20.0 ppm, O None
Methyl isobutyl ketone	108-10-1	21.0	A 75.0 ppm 15 min STEL, A 20.0 ppm, O 100.0 ppm
Mica	12001-26-2	None	A 3.0 mg/m ³ Respirable Dust, O 20.0 mppcf, O 3.0 mg/m ³ Respirable Dust
Molybdate/calcium	7789-82-4	None	A 3.0 mg/m ³ respirable particulate Mo, O 15.0 mg/m ³ TWA Total Dust
Monoazo pigment	12236-62-3	None	A 10.0 mg/m ³ inhalable dust particulate, O 15.0 mg/m ³ Total Dust, O 5.0 mg/m ³ Respirable Dust
N-butyl alcohol	71-36-3	6.0@68.0 °F	A 20.0 ppm, O 100.0 ppm, D 50.0 ppm 15 min TWA, D 25.0 ppm 8 & 12 hour TWA
N-pentyl propionate	624-54-4	1.5	A None, O None
Naphthalene	91-20-3	1.0@52.6 °C	A 15.0 ppm CEIL Skin, A 10.0 ppm Skin, O 10.0 ppm, D 0.1 ppm 8 & 12 hour TWA
Organic amide	Not Avail	None	A None, O None
Perylene maroon	5521-31-3	None	A None, O None
Phthalocyanine blue pigment-A	147-14-8	None	A 10.0 mg/m ³ inhalable dust PNO, A 3.0 mg/m ³ respirable particulate PNO, O 5.0 mg/m ³ TWA Respirable Dust PNOR, O 15.0 mg/m ³ Total Dust PNOR
Phthalocyanine blue pigment-B	68987-63-3	None	A None, O None
Phthalocyanine green	1328-53-6	None	A 3.0 mg/m ³ TWA Respirable Dust, A 10.0 mg/m ³ TWA inhalable dust, O 15.0 mg/m ³ TWA Total Dust, O 5.0 mg/m ³ TWA Respirable Dust
Pigment red 202	3089-17-6	None	A 3.0 mg/m ³ Respirable Dust, A 10.0 mg/m ³ inhalable dust PNOR, O 15.0 mg/m ³ , O 5.0 mg/m ³ Respirable Dust PNOR
Poly(oxy-1,2-ethanediyl).alpha.-[3-[3-(2h-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy phenyl	104810-48-2	None	A None, O None
Polyester resin-A	Not Avail	None	A None, O None
Polyester resin-B	129922-22-1	None	A None, O None
Polyester resin-C	68604-67-1	None	A None, O None
Polyester resin-D	69153-52-2	None	A None, O None
Polyethylene glycol	25322-68-3	None	A None, O None

INGREDIENTS	CAS #	VAPOR PRESSURE	EXPOSURE LIMITS
Polysiloxane modified aluminum-cerium hydroxide	Not Avail	None	A None, O None
Primary amyl acetate	628-63-7	4.2	A 100.0 ppm 15 min STEL, A 50.0 ppm, O 100.0 ppm
Proprietary copper compound	Not Avail	None	A None, O None
Propylene glycol monomethyl ether acetate	108-65-6	3.8	D 30.0 ppm 15 min TWA, A None, O None
Quinacridone pigment	1047-16-1	None	A 10.0 mg/m3 inhalable dust, O 15.0 mg/m3 Total Dust PNOR, O 5.0 mg/m3 Respirable Dust, D 10.0 mg/m3 Total Dust
Silver	7440-22-4	None	A None, O None
Stoddard solvent	8052-41-3	None	A 100.0 ppm, O 500.0 ppm TWA, D 100.0 ppm 15 min STEL, D 50.0 ppm 8 & 12 hour TWA
Substituted benzotriazole	25973-55-1	None	A None, O None
Synthetic resin-A	Not Avail	None	A None, O None
Synthetic resin-B	27925-07-1	None	A None, O None
T-butyl acetate	540-88-5	None	A 200.0 ppm, O 200.0 ppm
Tetraethyl orthosilicate	78-10-4	<2.0	A 10.0 ppm, O 100.0 ppm
Tin oxide	18282-10-5	None	A 2.0 mg/m3, O 2.0 mg/m3
Titanium dioxide	13463-67-7	None	O 15.0 mg/m3 Total Dust, D 10.0 mg/m3 8 & 12 hour TWA Total Dust, D 5.0 mg/m3 8 & 12 hour TWA Respirable Dust, A None
Titanium dioxide (rutile)	1317-80-2	None	A 10.0 mg/m3 TWA Total Dust, O 10.0 mg/m3 Total Dust, O 5.0 mg/m3 Respirable Dust, D 10.0 mg/m3 Total Dust, D 5.0 mg/m3 Respirable Dust
Toluene	108-88-3	22.0	A 20.0 ppm, O 300.0 ppm CEIL, O 500.0 ppm 10 min TWA, O 200.0 ppm, D 50.0 ppm 8 & 12 hour TWA Skin
Triethylenediamine	280-57-9	0.6@21.0 °C	A None, O None
Ultraviolet absorber	104810-47-1	None	A None, O None
Vm&p naphtha	8032-32-4	17.9@68.0 °F	A 300.0 ppm, D 100.0 ppm, O None
Weather resistant mixture	Not Avail	None	A None, O None
Wetting agents for solvent borne coatings	Not Avail	5.0	A None, O None
Xylene	1330-20-7	8.0@25.0 °C	A 150.0 ppm 15 min STEL, A 100.0 ppm, O 100.0 ppm, D 100.0 ppm 8 & 12 hour TWA
Yellow bismuth vandate pigment	14059-33-7	None	A None, O None
Zinc phosphate	7779-90-0	None	O 5.0 mg/m3 Respirable Dust, A None
Zirconium oxide	1314-23-4	None	A 10.0 mg/m3 15 min STEL, A 5.0 mg/m3, O 5.0 mg/m3 Zr

***A=ACGIH, O=OSHA, D=DuPont, S=Suppliers. Limits are 8 hour TWA unless otherwise specified. Vapor pressure @ 20° C unless otherwise noted. D=DuPont, Results obtained from E. I. du Pont de Nemours and Company.**

3. Hazards identification

Potential Health Effects:

Inhalation:

May cause nose and throat irritation. May cause nervous system depression, characterized by the following progressive steps: headache, dizziness, nausea, staggering gait, confusion, unconsciousness. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. If this product contains or is mixed with an isocyanate activator/hardener, the following health effects may apply: Exposure to isocyanates may cause respiratory sensitization. This effect may be permanent. Symptoms include an asthma-like reaction with shortness of breath, wheezing, cough or permanent lung sensitization. This effect may be delayed for several hours after exposure. Repeated overexposure to isocyanates may cause a decrease in lung function, which may be permanent. Individuals with lung or breathing problems or prior reactions to isocyanates must not be exposed to vapors or spray mist of this product.

Ingestion:

May result in gastrointestinal distress.

Skin or eye contact:

May cause irritation or burning of the eyes. Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis.

Other Potential Health Effects in addition to those listed above:

1,6-hexamethylene diisocyanate

Overexposure may cause asthma-like reactions with shortness of breath, wheezing, cough, which may be permanent; or permanent lung sensitization. This effect may be delayed for several hours after exposure. The following medical conditions may be aggravated by exposure: asthma, skin disorders, respiratory disorders.

Overexposure may cause damage to any of the following organs/systems: lungs, skin. Potential skin sensitizer that may cause allergic reactions and contact dermatitis resulting in severe irritation, dryness, and cracking of the skin.

2,4-pentanedione

2,4-pentanedione, a component of this product, is regulated by the U.S. EPA, under a significant new use rule. It is a violation of federal law to sell or use this product in consumer applications, including to private individuals, schools, and vocational schools. Can be absorbed through the skin in harmful amounts. Repeated exposures to

high concentrations has caused adverse health effects in laboratory animals. These effects involved the central nervous system, immune system, and the red blood cell forming system. No effect was seen at 100 ppm. The odor is disagreeable at a few ppm. Repeated or prolonged skin contact may cause any of the following: skin sensitization. Skin or eye contact may cause any of the following: irritation. Overexposure of this substance may cause effects on any of the following organs/systems: central nervous system, lungs, upper respiratory system, thymus.

4-chlorobenzotrifluoride

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: skin. Prolonged or repeated exposure may cause damage to any of the following organs/systems: kidneys, liver, thyroid. Potential skin sensitizer that may cause allergic reactions and contact dermatitis resulting in severe irritation, dryness, and cracking of the skin. Ingestion may cause any of the following: gastrointestinal irritation. Eye contact may cause any of the following: permanent eye injury. Inhalation may cause any of the following: stupor (central nervous system depression), respiratory tract irritation.

Acetic acid

Ingestion may cause any of the following: burns to mouth and stomach. Skin or eye contact may cause any of the following: irritation, burns.

Acetone

The following medical conditions may be aggravated by exposure: lung disease, eye disorders, skin disorders. Overexposure may cause damage to any of the following organs/systems: blood, central nervous system, eyes, kidneys, liver, respiratory system, skin.

Aliphatic polyisocyanate resin

Overexposure may cause asthma-like reactions with shortness of breath, wheezing, cough, which may be permanent; or permanent lung sensitization. This effect may be delayed for several hours after exposure. The following medical conditions may be aggravated by exposure: asthma, skin disorders, respiratory disorders. Potential skin sensitizer that may cause allergic reactions and contact dermatitis resulting in severe irritation, dryness, and cracking of the skin.

Aluminum salt

Eye contact may cause any of the following: irritation.

Aromatic hydrocarbon-A

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Aromatic hydrocarbon-B

The following medical conditions may be aggravated by exposure: skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Butyl acetate

May cause abnormal liver function. The following medical conditions may be aggravated by exposure: respiratory system. Tests for embryotoxic activity in animals has been inconclusive. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.

C.i. pigment yellow 154

Inhalation may cause any of the following: respiratory tract irritation. Skin or eye contact may cause any of the following: irritation.

Carbon black

Is an IARC, NTP or OSHA carcinogen. Has shown carcinogenic activity in laboratory animals at high doses. Significance to man is unknown. The following medical conditions may be aggravated by exposure: asthma, respiratory disease. WARNING: This chemical is known to the State of California to cause cancer.

Cumene

WARNING: This chemical is known to the State of California to cause cancer.

Diisobutyl ketone

The following medical conditions may be aggravated by exposure: asthma, blood, dermatitis. Contact may cause skin irritation with discomfort or rash. Repeated exposure may cause allergic skin rash, itching, swelling. This substance may cause damage to any of the following organs/systems: eyes, kidneys, liver. Extremely high oral and inhalation doses in laboratory animals have shown weight changes in various organs such as the liver, kidney, brain, heart and adrenal gland. In addition liver and kidney injury were observed at the extremely high inhalation level. In another inhalation study there was a slight depression in the white blood cell count. Liquid or vapor causes irritation, experienced as stinging, excess blinking and tear production, with excess redness and swelling of the conjunctiva.

Ethyl acetate

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: eyes, respiratory system, skin. Tests in laboratory animals have shown effects on any of the following organs/systems: blood, kidneys, liver.

Ethylbenzene

Is an IARC, NTP or OSHA carcinogen. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. Studies in laboratory animals have shown reproductive, embryotoxic and developmental effects. WARNING: This chemical is known to the State of California to cause cancer.

Ethylene glycol monobutyl ether

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, central nervous system, eyes, gastrointestinal system, kidneys, liver, respiratory system, skin. May cause injury to the kidneys, liver, blood and/or bone marrow. Repeated overexposure may result in damage to the blood. Eye contact may cause corneal injury. If absorbed through the skin, may be: harmful.

Ethylene glycol monobutyl ether acetate

May destroy red blood cells. May cause abnormal kidney function. May cause temporary upper respiratory and/or lung irritation with cough, difficult breathing, or shortness of breath. The following medical conditions may be aggravated by exposure: central nervous system, gastrointestinal system, kidneys, liver, dermatitis. Can be absorbed through the skin in harmful amounts. Overexposure may cause damage to any of the following organs/systems: blood, kidneys, liver. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness.

Heavy mineral spirits

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Heptane

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, respiratory system, skin. May cause central nervous system effects such as dizziness, headache, nausea, and loss of consciousness. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors. Aspiration may occur during swallowing or vomiting, resulting in lung damage.

Hydrotreated heavy naphtha (petroleum)-A

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Hydrotreated heavy naphtha (petroleum)-B

Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Isopropyl alcohol

The following medical conditions may be aggravated by exposure: dermatitis, respiratory disease. Developmental toxicity was seen in rat's offspring at doses that were maternally toxic. Contact may cause skin irritation with discomfort or rash. Can be absorbed through the skin in harmful amounts. Contact will cause moderate to severe redness and swelling, itching, tingling sensation, painful burning. May cause injury to the cornea of the eyes. Prolonged or repeated exposure may cause damage to any of the following organs/systems: liver. Ingestion studies on laboratory animals showed that very high oral doses caused increased liver and kidney weights. Aspiration may occur during swallowing or vomiting, resulting in lung damage. May cause central nervous system depression with headache, stupor, uncoordinated or strange behavior, or unconsciousness. Irritating to the mouth, throat and stomach. May cause irritation of the respiratory tract, experienced as nasal discomfort and discharge, coughing and possibly accompanied by chest pain. Prolonged or repeated skin contact may cause drying, cracking, or irritation. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness. Swallowing significant amounts of substance could cause serious injury, even death.

Kaolin

The following medical conditions may be aggravated by exposure: asthma, dermatitis. Repeated or prolonged inhalation may cause any of the following: lung injury.

Light yellow lemon yellow oxide pigment

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Methyl ethyl ketone

Material is irritating to mucous membranes and upper respiratory tract. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, eyes, respiratory system, skin. Prolonged or repeated overexposure may cause any of the following: conjunctivitis, dermatitis. High concentrations have caused embryotoxic effects in laboratory animals. Aspiration may occur during swallowing or vomiting, resulting in lung damage. Ingestion may cause headache, nausea, vomiting, dizziness, and drowsiness.

Methyl isobutyl ketone

Is an IARC, NTP or OSHA carcinogen. WARNING: This chemical is known to the State of California to cause cancer and birth defects or other reproductive harm

Mica

Repeated or prolonged inhalation may cause any of the following: lung irritation. Long-term respiratory exposure exceeding TLV may damage the lungs, leading to bronchitis and impairment of lung capacity.

Molybdate/calcium

If ingested, may be: harmful or fatal.

N-butyl alcohol

May cause abnormal blood forming function with anemia. Liquid splashes in the eye may result in chemical burns.

Naphthalene

Is an IARC, NTP or OSHA carcinogen. Tests in some laboratory animals demonstrate carcinogenic activity. Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: kidneys, liver. Recurrent overexposure may result in liver and kidney injury. WARNING: This chemical is known to the State of California to cause cancer.

Organic amide

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Poly(oxy-1,2-ethanediy),.alpha.-[3-[3-(2h-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy phenyl

The following medical conditions may be aggravated by exposure: jaundice, liver disease, allergies, kidney disorders, skin disorders. Skin contact may cause any of the following: allergic contact dermatitis.

Polyester resin-D

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Proprietary copper compound

Contact may cause skin irritation with discomfort or rash. May cause eye irritation with discomfort, tearing, or blurred vision.

Propylene glycol monomethyl ether acetate

Recurrent overexposure may result in liver and kidney injury.

Stoddard solvent

The following medical conditions may be aggravated by exposure: asthma, skin disorders. Laboratory studies with rats have shown that petroleum distillates can cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Substituted benzotriazole

The following medical conditions may be aggravated by exposure: jaundice, liver disease. Repeated or prolonged ingestion may cause any of the following: changes in the blood, liver effects.

T-butyl acetate

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, eyes, gastrointestinal system, liver, skin.

Tetraethyl orthosilicate

Overexposure may cause damage to any of the following organs/systems: kidneys, liver, lungs.

Titanium dioxide

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m³ respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m³ level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium Dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.'

Titanium dioxide (rutile)

Is an IARC, NTP or OSHA carcinogen. In a lifetime inhalation test, lung cancers were found in some rats exposed to 250 mg/m³ respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250 mg/m³ level are not relevant to the workplace. Results of a DuPont epidemiology study showed that employees who had been exposed to Titanium Dioxide were at no greater risk of developing lung cancer than were employees who had not been exposed to Titanium dioxide. No pulmonary fibrosis was found in any of the employees and no association was observed between Titanium dioxide exposure and chronic respiratory disease or x-ray abnormalities. Based on the results of this study DuPont concludes that titanium dioxide will not cause lung cancer or chronic respiratory disease in humans at concentrations experienced in the workplace.'

Toluene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, respiratory system, skin. Can be absorbed through the skin in harmful amounts. Recurrent overexposure may result in liver and kidney injury. High airborne levels have produced irregular heart beats in animals and occasional palpitations in humans. Rats exposed to very high airborne levels have exhibited high frequency hearing deficits. The significance of this to man is unknown. WARNING: This chemical is known to the State of California to cause birth defects or other reproductive harm.

Ultraviolet absorber

The following medical conditions may be aggravated by exposure: jaundice, liver disease, allergies, kidney disorders, skin disorders. Skin contact may cause any of the following: allergic contact dermatitis.

Vm&p naphtha

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: central nervous system, kidneys, liver, lungs, respiratory system, skin. This substance may cause damage to any of the following organs/systems: central nervous system, kidneys, liver, lungs, skin and eyes. Material may be harmful or fatal if swallowed.

Xylene

Increased susceptibility to the effects of this material may be observed in people with preexisting disease of any of the following: bone marrow, cardiovascular system, central nervous system, kidneys, liver, lungs. Recurrent overexposure may result in liver and kidney injury. High exposures may produce irregular heart beats. Canada classifies Xylene as a developmental toxin as high exposures to xylenes in some animal studies have been reported to cause health effects on the developing fetus/embryo. These effects were often at levels toxic to the adult animal. The significance of these effects to humans is not known. Repeated or prolonged skin contact may cause any of the following: irritation, dryness, cracking of the skin.

4. First aid measures**First Aid Procedures:****Inhalation:**

If affected by inhalation of vapor or spray mist, move to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. If breathing difficulty persists, or occurs later, consult a physician.

Ingestion:

In the unlikely event of ingestion, DO NOT INDUCE VOMITING. Call a physician immediately and have names of ingredients available.

Skin or eye contact:

In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash thoroughly with soap and water. If irritation occurs, contact a physician.

5. Firefighting measures

Flash Point (Closed Cup):

See Section 11 for exact values.

Flammable Limits: LFL 0.5 % UFL 16 %

Extinguishing Media:

Universal aqueous film-forming foam, carbon dioxide, dry chemical.

Fire Fighting Procedures:

Full protective equipment, including self-contained breathing apparatus, is recommended. Water from fog nozzles may be used to prevent pressure build-up.

Fire and Explosion Hazards:

For flammable liquids, vapor/air will ignite when an ignition source is present. In other cases, when heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

6. Accidental release measures

Procedures for cleaning up spills or leaks:

Ventilate area. Remove sources of ignition. Prevent skin and eye contact and breathing of vapor. If material does not contain or is not mixed with an isocyanate activator/hardener: Wear a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH approved TC-23C), eye protection, gloves and protective clothing. Confine, remove with inert absorbent, and dispose of properly. If the material contains, or is mixed with an isocyanate activator/hardener: Wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C), eye protection, gloves and protective clothing. Pour liquid decontamination solution over the spill and allow to sit at least 10 minutes. Typical decontamination solutions for isocyanate containing materials are: 20% Surfactant (Tergitol TMN 10) and 80% Water OR 0-10% Ammonia, 2-5% Detergent and Water (balance). Pressure can be generated. Do not seal waste containers for 48 hours to allow CO2 to vent. After 48 hours, material may be sealed and disposed of properly.

Ecological information:

There is no data available on the product. The product should not be allowed to enter drains, water courses or the soil.

7. Handling and storage

Precautions to be taken in handling and storing:

Observe label precautions. If combustible (flashpoint between 38-93 deg C or 100 - 200 deg F), keep away from heat, sparks and flame. If flammable (flashpoint less than 38 deg C or 100 deg F), also keep away from static discharges and other sources of ignition. If material is extremely flammable (flashpoint less than - 8 deg C or 20 deg F) or flammable, VAPORS MAY IGNITE EXPLOSIVELY OR CAUSE FLASH FIRE, respectively. Vapors may spread long distances. Prevent buildup of vapors. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 49 deg C or 120 deg F. If product is waterbased, do not freeze.

Other precautions:

If material is a coating: do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves. Combustible dust clouds may be created where operations produce fine material (dust). Avoid formation of significant deposits of material as they may become airborne and form combustible dust clouds. Handling and processing operations should be conducted in accordance with best practices (e.g.NFPA-654).

8. Exposure controls/personal protection

Ventilation:

Provide sufficient ventilation in volume and pattern to keep contaminants below applicable exposure limits.

Respiratory protection:

Do not breathe vapors or mists. If this product contains isocyanates or is used with an isocyanate activator/hardener, wear a positive-pressure, supplied-air respirator (NIOSH approved TC-19C) while mixing activator/hardener with paint, during application and until all vapors and spray mist are exhausted. If product does not contain or is not mixed with an isocyanate activator/hardener, a properly fitted air-purifying respirator with organic vapor cartridges (NIOSH TC-23C) and particulate filter (NIOSH TC-84A) may be used. Follow respirator manufacturer's directions for respirator use. Do not permit anyone without protection in the painting area. Individuals with history of lung or breathing problems or prior reaction to isocyanates should not use or be exposed vapor or spray mist if product contains or is mixed with isocyanate activators/hardeners.

Protective equipment:

Personal protective equipment should be worn to prevent contact with eyes, skin or clothing.

Skin and body protection:

Neoprene gloves and coveralls are recommended.

Desirable in all industrial situations. Goggles are preferred to prevent eye irritation. If safety glasses are substituted, include splash guard or side shields.

9. Physical and chemical properties

Evaporation rate	Slower than Ether
Water solubility	NIL
Vapour density	Heavier than air
Approx. Boiling Range (°C)	56 – 203 °C
Approx. Freezing Range (°C)	-134 °C
Gallon Weight (lbs/gal)	6.81819 - 26.1211
Specific Gravity	0.82 - 3.13
Percent Volatile By Volume	7.06 - 100.00
Percent Volatile By Weight	5.00 - 100.00
Percent Solids By Volume	0.00 - 92.94
Percent Solids By Weight	0.00 - 95.00

10. Stability and reactivity**Stability:**

Stable

Incompatibility (materials to avoid):

None reasonably foreseeable

Hazardous decomposition products:CO, CO₂, smoke, and oxides of any heavy metals that are reported in "Composition, Information on Ingredients" section.**Hazardous Polymerization:**

Will not occur.

Sensitivity to Static Discharge:

For flammable materials (flashpoint less than 38 deg C or 100 deg F) and combustibles (flashpoint between 38- 93 deg C or 100-200 deg F) if heated above the flashpoint, solvent vapors in air may explode if static grounding and bonding is not used during transfer of this product.

Sensitivity to Mechanical Impact:

None known.

11. Additional Information

1001S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(26.5%), Weather resistant mixture **GAL WT: 20.75 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 76.56 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1002S™ Heavy mineral spirits, Iron oxide, Mica, Polysiloxane modified aluminum-cerium hydroxide **GAL WT: 20.20 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 74.34 SOLVENT DENSITY: 6.50 VOC LE: 2.0 VOC AP: 2.0 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1003S™ Ethylene glycol monobutyl ether(10%), Iron oxide, Mica, Weather resistant mixture **GAL WT: 21.60 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 71.16 SOLVENT DENSITY: 7.53 VOC LE: 2.2 VOC AP: 2.2 FLASH POINT: No measurable H: 2 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1004S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(44.0%), Weather resistant mixture **GAL WT: 21.19 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 71.74 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1005S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(36.0%), Weather resistant mixture **GAL WT: 20.75 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 72.38 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: Above 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1006S™ Ethylene glycol monobutyl ether(10%), Iron oxide, Mica, Weather resistant mixture **GAL WT: 21.60 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 75.46 SOLVENT DENSITY: 7.53 VOC LE: 2.2 VOC AP: 2.2 FLASH POINT: Above 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1007S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(43.0%), Weather resistant mixture **GAL WT: 21.19 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 71.79 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1009S™ Heavy mineral spirits, Mica, Titanium dioxide (rutile)(50.7%) **GAL WT: 21.60 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 73.03 SOLVENT DENSITY: 6.50 VOC LE: 2.2 VOC AP: 2.2 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1014S™ Ethylene glycol monobutyl ether(10%), Mica, Titanium dioxide(40.0%), Weather resistant mixture **GAL WT: 20.83 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 72.30 SOLVENT DENSITY: 7.53 VOC LE: 2.1 VOC AP: 2.1 FLASH POINT: No measurable H: 2 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

1052S™ Amorphous silica-A, Heavy mineral spirits, Tin oxide, Titanium dioxide(31.0%), Weather resistant mixture, Zirconium oxide **GAL WT: 17.44 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 77.02 SOLVENT DENSITY: 6.50 VOC LE: 1.7 VOC AP: 1.7 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA**

STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

1053S™ Amorphous silica-A, Heavy mineral spirits, Iron oxide, Weather resistant mixture, Zirconium oxide GAL WT: 15.40 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 79.16 SOLVENT DENSITY: 6.50 VOC LE: 1.5 VOC AP: 1.5 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

1054S™ Amorphous silica-A, Heavy mineral spirits, Tin oxide, Titanium dioxide(38.0%), Weather resistant mixture, Zirconium oxide GAL WT: 17.94 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 76.53 SOLVENT DENSITY: 6.50 VOC LE: 1.8 VOC AP: 1.8 FLASH POINT: 141 °F - 200 °F H: 1 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

1055S™ Heavy mineral spirits, Mica, Polysiloxane modified aluminum-cerium hydroxide, Titanium dioxide (rutile)(42.7%) GAL WT: 26.12 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 72.18 SOLVENT DENSITY: 7.50 VOC LE: 2.6 VOC AP: 2.6 FLASH POINT: 141 °F - 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIA TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

1056S™ Amorphous silica-A, Heavy mineral spirits, Tin oxide, Titanium dioxide(10.1%), Weather resistant mixture, Zirconium oxide GAL WT: 17.94 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 76.53 SOLVENT DENSITY: 6.50 VOC LE: 1.8 VOC AP: 1.8 FLASH POINT: No measurable H: 1 F: 2 R: 0 OSHA STORAGE: N/A TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

1057S™ Heavy mineral spirits, Iron oxide, Mica, Polysiloxane modified aluminum-cerium hydroxide, Titanium dioxide (rutile)(24.2%) GAL WT: 24.20 WT PCT SOLIDS: 90.00 VOL PCT SOLIDS: 70.72 SOLVENT DENSITY: 6.50 VOC LE: 2.4 VOC AP: 2.4 FLASH POINT: Above 200 °F H: 2 F: 2 R: 0 OSHA STORAGE: IIIB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

15303S™ Aliphatic polyisocyanate resin, Butyl acetate, Methyl acetate, Methyl isoamyl ketone GAL WT: 8.80 WT PCT SOLIDS: 66.00 VOL PCT SOLIDS: 59.54 SOLVENT DENSITY: 7.40 VOC LE: 1.9 VOC AP: 1.5 FLASH POINT: 20 °F to below 73 °F H: 3 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

15305S™ 4,6-dimethyl-2-heptanone, Aliphatic polyisocyanate resin, Diisobutyl ketone, Methyl acetate, Methyl amyl ketone GAL WT: 8.72 WT PCT SOLIDS: 66.00 VOL PCT SOLIDS: 58.94 SOLVENT DENSITY: 7.21 VOC LE: 1.9 VOC AP: 1.5 FLASH POINT: 20 °F to below 73 °F H: 3 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

15307S™ 2-ethylhexyl acetate, 4,6-dimethyl-2-heptanone, Aliphatic polyisocyanate resin, Diisobutyl ketone, Methyl acetate GAL WT: 8.79 WT PCT SOLIDS: 66.00 VOL PCT SOLIDS: 59.42 SOLVENT DENSITY: 7.35 VOC LE: 1.9 VOC AP: 1.5 FLASH POINT: 20 °F to below 73 °F H: 3 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

15308S™ 2-ethylhexyl acetate, 4-chlorobenzotrifluoride, Aliphatic polyisocyanate resin, Dimethyl glutarate, Methyl acetate GAL WT: 9.20 WT PCT SOLIDS: 66.00 VOL PCT SOLIDS: 62.21 SOLVENT DENSITY: 8.28 VOC LE: 1.9 VOC AP: 1.6 FLASH POINT: 20 °F to below 73 °F H: 3 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

15309S™ 1,6-hexamethylene diisocyanate(0.1%*®), Aliphatic polyisocyanate resin, Methyl acetate GAL WT: 9.25 WT PCT SOLIDS: 80.00 VOL PCT SOLIDS: 76.27 SOLVENT DENSITY: 7.80 VOC LE: 0.0 VOC AP: 0.0 FLASH POINT: 20 °F to below 73 °F H: 3 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

15375S™ Acetone, Ethyl 3-ethoxy propionate, Ethyl acetate, Methyl ethyl ketone GAL WT: 6.93 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 6.93 VOC LE: 7.2 VOC AP: 3.9 FLASH POINT: Below 20 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

15385S™ 1,2,4-trimethyl benzene(3%*), Acetone, Aromatic hydrocarbon-B, Butyl acetate, Cumene(0.2%*®), Methyl isoamyl ketone, Propylene glycol monomethyl ether acetate GAL WT: 7.02 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 7.02 VOC LE: 7.3 VOC AP: 4.1 FLASH POINT: Below 20 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

15395S™ 2-ethylhexyl acetate, Acetone, Ethyl acetate, Methyl ethyl ketone GAL WT: 6.95 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 6.95 VOC LE: 7.2 VOC AP: 4.2 FLASH POINT: Below 20 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

15397S™ 2-ethylhexyl acetate, Acetone, Methyl amyl ketone GAL WT: 6.92 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 6.92 VOC LE: 7.1 VOC AP: 4.1 FLASH POINT: Below 20 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

15399S™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Butyl acetate, Dimethyl glutarate, Isopropyl alcohol, Methyl amyl ketone GAL WT: 7.96 WT PCT SOLIDS: 52.49 VOL PCT SOLIDS: 46.57 SOLVENT DENSITY: 6.91 VOC LE: 3.5 VOC AP: 3.3 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

15P85002™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-A, Aromatic hydrocarbon-A, Butyl acetate, Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Naphthalene(0.2%*®), Polyester resin-A, Titanium dioxide(24.0%) GAL WT: 10.09 WT PCT SOLIDS: 62.94 VOL PCT SOLIDS: 47.91 SOLVENT DENSITY: 7.17 VOC LE: 3.5 VOC AP: 3.3 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

15R0001EZ™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-C, Acrylic resin, Aromatic hydrocarbon-A, Butyl acetate, Carbon black(1.2%), Ethyl acetate, Methyl amyl ketone, Naphthalene(0.2%*®), Polyester resin-A GAL WT: 8.24 WT PCT SOLIDS: 53.43 VOL PCT SOLIDS: 47.01 SOLVENT DENSITY: 7.34 VOC LE: 3.7 VOC AP: 3.6 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

194S™ 2-ethylhexyl acetate, Aliphatic polyisocyanate resin, Butyl acetate, Ethyl acetate **GAL WT: 9.05 WT PCT SOLIDS: 75.00 VOL PCT SOLIDS: 69.53 SOLVENT DENSITY: 7.43 VOC LE: 2.3 VOC AP: 2.3 FLASH POINT: 20 °F to below 73 °F H: 3 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

196S™ Acetone, Aliphatic polyisocyanate resin, Ethyl acetate **GAL WT: 8.58 WT PCT SOLIDS: 64.27 VOL PCT SOLIDS: 56.42 SOLVENT DENSITY: 7.03 VOC LE: 2.0 VOC AP: 1.5 FLASH POINT: Below 20 °F H: 3 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

197S™ Aliphatic polyisocyanate resin, Methyl amyl ketone **GAL WT: 9.55 WT PCT SOLIDS: 95.00 VOL PCT SOLIDS: 92.94 SOLVENT DENSITY: 6.79 VOC LE: 0.5 VOC AP: 0.5 FLASH POINT: 100 °F - 141 °F H: 3 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

359S™ 1,2,4-trimethyl benzene(8%*), 1,3,5-trimethyl benzene, Acrylic polymer-A, Aromatic hydrocarbon-B, Butyl acetate, Cumene(0.4%* @) **GAL WT: 7.99 WT PCT SOLIDS: 25.01 VOL PCT SOLIDS: 20.27 SOLVENT DENSITY: 7.68 VOC LE: 6.0 VOC AP: 6.0 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

389S™ 2,4-pentanedione, Dibutyl tin dilaurate **GAL WT: 8.14 WT PCT SOLIDS: 1.00 VOL PCT SOLIDS: 0.94 SOLVENT DENSITY: 8.14 VOC LE: 8.1 VOC AP: 8.1 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

45P784083EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-C, Acrylic resin, Butyl acetate, Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Methyl ethyl ketone, Methyl isoamyl ketone, Phthalocyanine blue pigment-A, Polyester resin-A, Propylene glycol monomethyl ether acetate, Titanium dioxide(5.2%) **GAL WT: 8.55 WT PCT SOLIDS: 54.50 VOL PCT SOLIDS: 45.65 SOLVENT DENSITY: 7.15 VOC LE: 3.7 VOC AP: 3.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

45P855731EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Butyl acetate, Carbon black(1.0%), Ethyl acetate, Iron oxide, Isoindolinone pigment, Isopropyl alcohol, Methyl amyl ketone, Methyl ethyl ketone, Methyl isoamyl ketone, Polyester resin-A, Propylene glycol monomethyl ether acetate **GAL WT: 8.40 WT PCT SOLIDS: 53.99 VOL PCT SOLIDS: 45.84 SOLVENT DENSITY: 7.14 VOC LE: 3.7 VOC AP: 3.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

45P9188EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-C, Acrylic resin, Aluminum hydroxide, Amorphous silica-A, Butyl acetate, Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Methyl isoamyl ketone, Polyester resin-A, Propylene glycol monomethyl ether acetate, Titanium dioxide(31.1%) **GAL WT: 10.85 WT PCT SOLIDS: 65.24 VOL PCT SOLIDS: 47.55 SOLVENT DENSITY: 7.18 VOC LE: 3.6 VOC AP: 3.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

45PN0786EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Aluminum hydroxide, Amorphous silica-A, Butyl acetate, Ethyl acetate, Methyl amyl ketone, Methyl isoamyl ketone, Polyester resin-A, Propylene glycol monomethyl ether acetate, Titanium dioxide(37.4%) **GAL WT: 11.59 WT PCT SOLIDS: 67.14 VOL PCT SOLIDS: 47.12 SOLVENT DENSITY: 7.19 VOC LE: 3.6 VOC AP: 3.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

45R0001EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Aromatic hydrocarbon-A, Butyl acetate, Carbon black(1.7%), Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Polyester resin-A, Primary amyl acetate **GAL WT: 8.24 WT PCT SOLIDS: 53.78 VOL PCT SOLIDS: 47.22 SOLVENT DENSITY: 7.39 VOC LE: 3.7 VOC AP: 3.7 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

45R0006EX™ Acetone, Acrylic polymer-A, Acrylic resin, Aluminum hydroxide, Amorphous silica-A, Butyl acetate, Isopropyl alcohol, Methyl amyl ketone, Methyl isoamyl ketone, Polyester resin-A, Propylene glycol monomethyl ether acetate, Titanium dioxide(29.0%) **GAL WT: 10.52 WT PCT SOLIDS: 63.00 VOL PCT SOLIDS: 45.40 SOLVENT DENSITY: 7.12 VOC LE: 3.6 VOC AP: 3.3 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

500S™ 1,2,4-trimethyl benzene(3%*), Acetone, Acrylic polymer-A, Aromatic hydrocarbon-B, Butyl acetate, Cumene(0.2%* @), Ethylbenzene(1.3%* @), Methyl amyl ketone, Methyl ethyl ketone, Methyl isoamyl ketone, N-pentyl propionate, Xylene(5%* @) **GAL WT: 7.69 WT PCT SOLIDS: 38.93 VOL PCT SOLIDS: 31.88 SOLVENT DENSITY: 6.90 VOC LE: 4.3 VOC AP: 3.4 FLASH POINT: Below 20 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

6210E™ 2,4-pentanedione, Acetone, Acrylic polymer-A, Butyl acetate, Ethylbenzene(0.2%* @), Heptane, Hydrotreated heavy naphtha (petroleum)-B, Methyl amyl ketone, N-butyl alcohol(4%*), Polyester resin-B, Synthetic resin-B, T-butyl acetate **GAL WT: 8.05 WT PCT SOLIDS: 57.24 VOL PCT SOLIDS: 50.14 SOLVENT DENSITY: 6.93 VOC LE: 3.3 VOC AP: 3.2 VOC LE (TBAC): 2.7 VOC AP (TBAC): 2.2 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

6340S™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-A, Butyl acetate, Ethyl acetate, Hydrotreated heavy naphtha (petroleum)-B, Isopropyl alcohol, Methyl amyl ketone **GAL WT: 7.93 WT PCT SOLIDS: 51.94 VOL PCT SOLIDS: 44.74 SOLVENT DENSITY: 6.87 VOC LE: 3.7 VOC AP: 3.6 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7200E™ Acrylic polymer-A, Acrylic resin, Amorphous silica-B, Butyl acetate, Ethyl acetate, Heptane, Isopropyl alcohol, Methyl amyl ketone, Polyester resin-B **GAL WT: 7.99 WT PCT SOLIDS: 52.35 VOL PCT SOLIDS: 43.70 SOLVENT DENSITY: 6.75 VOC LE: 3.8 VOC AP: 3.8 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7285S™ 2-ethylhexyl acetate, Acetone, Ethyl acetate, Methyl ethyl ketone **GAL WT: 7.27 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 7.27 VOC LE: 7.4 VOC AP: 6.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7300E™ 1,2,4-trimethyl benzene(1%*), Aromatic hydrocarbon-B, Bis(1,2,2,6,6-pentamethyl-4-piperidinyl) sebacate, Ethyl 3-ethoxy propionate, Ethyl acetate, Methyl isobutyl ketone(4.2%*@), Polyester resin-C, Propylene glycol monomethyl ether acetate, Toluene(5%*@) **GAL WT: 8.66 WT PCT SOLIDS: 51.82 VOL PCT SOLIDS: 45.68 SOLVENT DENSITY: 7.69 VOC LE: 4.2 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

7385S™ 2-ethylhexyl acetate, Acetone, Ethyl acetate, Propylene glycol monomethyl ether acetate **GAL WT: 7.54 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 7.55 VOC LE: 7.6 VOC AP: 7.0 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7400E™ Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-B, Butyl acetate, Isopropyl alcohol, Methyl acetate, Methyl amyl ketone, Synthetic resin-B **GAL WT: 7.89 WT PCT SOLIDS: 43.28 VOL PCT SOLIDS: 34.73 SOLVENT DENSITY: 6.85 VOC LE: 4.1 VOC AP: 3.5 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7410E™ Acetone, Acrylic polymer-A, Butyl acetate, Ethyl acetate, Heptane, Methyl acetate, Methyl amyl ketone, Polyester resin-D, Synthetic resin-B **GAL WT: 8.43 WT PCT SOLIDS: 66.57 VOL PCT SOLIDS: 60.37 SOLVENT DENSITY: 7.05 VOC LE: 2.0 VOC AP: 1.7 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

74441EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-C, Amorphous silica-A, Butyl acetate, Carbon black(0.1%), Ethyl acetate, Methyl amyl ketone, Methyl isoamyl ketone, Polyester resin-A, Propylene glycol monomethyl ether acetate, Titanium dioxide(21.9%) **GAL WT: 9.77 WT PCT SOLIDS: 59.27 VOL PCT SOLIDS: 44.34 SOLVENT DENSITY: 7.14 VOC LE: 3.7 VOC AP: 3.2 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

74442EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Butyl acetate, Carbon black(1.0%), Ethyl acetate, Iron oxide, Isoindolinone pigment, Isopropyl alcohol, Methyl amyl ketone, Methyl ethyl ketone, Polyester resin-A, Propylene glycol monomethyl ether acetate **GAL WT: 8.43 WT PCT SOLIDS: 55.02 VOL PCT SOLIDS: 46.83 SOLVENT DENSITY: 7.12 VOC LE: 3.5 VOC AP: 3.2 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7700E™ Acrylic polymer-A, Acrylic resin, Amorphous silica-A, Butyl acetate, Ethyl acetate, Heptane, Isopropyl alcohol, Methyl amyl ketone, Polyester resin-B **GAL WT: 8.03 WT PCT SOLIDS: 52.53 VOL PCT SOLIDS: 45.86 SOLVENT DENSITY: 7.15 VOC LE: 3.8 VOC AP: 3.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7710E™ Ethyl acetate, Methyl ethyl ketone, Polyester resin-B **GAL WT: 8.89 WT PCT SOLIDS: 89.75 VOL PCT SOLIDS: 87.43 SOLVENT DENSITY: 7.26 VOC LE: 0.9 VOC AP: 0.9 FLASH POINT: 20 °F to below 73 °F H: 1 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

775115EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-C, Acrylic resin, Butyl acetate, Carbon black(0.4%), Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Methyl ethyl ketone, Methyl isoamyl ketone, Polyester resin-A, Propylene glycol monomethyl ether acetate, Titanium dioxide(9.6%) **GAL WT: 8.86 WT PCT SOLIDS: 57.60 VOL PCT SOLIDS: 47.39 SOLVENT DENSITY: 7.14 VOC LE: 3.6 VOC AP: 3.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7800E™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-C, Butyl acetate, Methyl ethyl ketone, Polyester resin-A **GAL WT: 8.57 WT PCT SOLIDS: 73.02 VOL PCT SOLIDS: 68.11 SOLVENT DENSITY: 7.25 VOC LE: 2.2 VOC AP: 2.2 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7810E™ Acetone, Acrylic polymer-C, Acrylic resin, Amorphous silica-B, Butyl acetate, Isopropyl alcohol, Methyl amyl ketone, Methyl ethyl ketone, Polyester resin-A, Substituted benzotriazole **GAL WT: 8.44 WT PCT SOLIDS: 67.53 VOL PCT SOLIDS: 61.27 SOLVENT DENSITY: 7.08 VOC LE: 2.7 VOC AP: 2.6 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7900E™ Acetone, Acrylic polymer-A, Butyl acetate, Methyl ethyl ketone, Polyester resin-A **GAL WT: 8.50 WT PCT SOLIDS: 70.62 VOL PCT SOLIDS: 65.55 SOLVENT DENSITY: 7.25 VOC LE: 2.4 VOC AP: 2.3 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

7910E™ Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-B, Butyl acetate, Isopropyl alcohol, Methyl amyl ketone, Methyl ethyl ketone, Polyester resin-A **GAL WT: 8.40 WT PCT SOLIDS: 66.36 VOL PCT SOLIDS: 60.11 SOLVENT DENSITY: 7.09 VOC LE: 2.8 VOC AP: 2.7 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

817U™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Amorphous silica-A, Butyl acetate, Ethyl 3-ethoxy propionate, Ethyl acetate, Methyl amyl ketone, Methyl isobutyl ketone(1.1%*@), Polyester resin-C, Propylene glycol monomethyl ether acetate, Titanium dioxide(22.7%), Toluene(1%*@) **GAL WT: 10.03 WT PCT SOLIDS: 53.77 VOL PCT SOLIDS: 37.91 SOLVENT DENSITY: 7.46 VOC LE: 4.6 VOC AP: 4.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

8200E™ Acrylic polymer-A, Acrylic resin, Amorphous silica-B, Butyl acetate, Ethyl acetate, Heptane, Isopropyl alcohol, Methyl amyl ketone, Polyester resin-B **GAL WT: 7.99 WT PCT SOLIDS: 52.35 VOL PCT SOLIDS: 43.70 SOLVENT DENSITY: 6.75 VOC LE: 3.8 VOC AP: 3.8 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

8285S™ Ethyl acetate, Heptane **GAL WT: 7.22 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 7.22 VOC LE: 7.2 VOC AP: 7.2 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

8295S™ Acetone, Butanedioic acid, dimethyl ester, Dimethyl glutarate, Heptane, Hexanedioic acid, dimethyl ester, Isopropyl alcohol, Methyl amyl ketone, Vm&p naphtha **GAL WT: 6.82 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 6.82 VOC LE: 6.8 VOC AP: 6.0 FLASH POINT: Below 20 °F H: 2 F: 3 R: 0**

OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8400E™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-B, Acrylic resin, Butyl acetate, Dimethyl glutarate, Isopropyl alcohol, Methyl amyl ketone, Polyester resin-A GAL WT: 8.03 WT PCT SOLIDS: 51.70 VOL PCT SOLIDS: 44.32 SOLVENT DENSITY: 6.97 VOC LE: 3.7 VOC AP: 3.5 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8401EG™ Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-B, Butyl acetate, Ethyl acetate, Ethylbenzene(0.2%* @), Isopropyl alcohol, Methyl amyl ketone, Polyester resin-D, Synthetic resin-A GAL WT: 8.10 WT PCT SOLIDS: 50.15 VOL PCT SOLIDS: 43.49 SOLVENT DENSITY: 7.20 VOC LE: 3.9 VOC AP: 3.8 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8405S™ 4,6-dimethyl-2-heptanone, Aliphatic polyisocyanate resin, Butyl acetate, Diisobutyl ketone, Methyl amyl ketone GAL WT: 8.51 WT PCT SOLIDS: 65.00 VOL PCT SOLIDS: 56.65 SOLVENT DENSITY: 6.88 VOC LE: 3.0 VOC AP: 3.0 FLASH POINT: 73 °F to below 100 °F H: 3 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8407S™ Aliphatic polyisocyanate resin, Butyl acetate, Diisobutyl ketone, Methyl amyl ketone, N-pentyl propionate GAL WT: 8.53 WT PCT SOLIDS: 65.00 VOL PCT SOLIDS: 56.80 SOLVENT DENSITY: 6.92 VOC LE: 3.0 VOC AP: 3.0 FLASH POINT: 73 °F to below 100 °F H: 3 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8420S™ 1,2,4-trimethyl benzene(2%*), Acetone, Acrylic polymer-A, Acrylic resin, Aromatic hydrocarbon-B, Butyl acetate, Cumene(0.1%* @), Diisobutyl ketone, Methyl amyl ketone, Polyester resin-A GAL WT: 8.06 WT PCT SOLIDS: 50.12 VOL PCT SOLIDS: 42.29 SOLVENT DENSITY: 6.97 VOC LE: 3.7 VOC AP: 3.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

8430S™ Acetone, Acrylic polymer-A, Acrylic resin, Butyl acetate, Ethyl acetate, Methyl amyl ketone, Methyl isoamyl ketone, N-pentyl propionate, Polyester resin-B, Synthetic resin-A GAL WT: 7.99 WT PCT SOLIDS: 49.90 VOL PCT SOLIDS: 42.19 SOLVENT DENSITY: 6.94 VOC LE: 3.7 VOC AP: 3.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8475S™ Butyl acetate, Ethyl acetate GAL WT: 7.51 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 7.51 VOC LE: 7.5 VOC AP: 7.5 FLASH POINT: 20 °F to below 73 °F H: 1 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8821S™ 4-chlorobenzotrifluoride, Acetone, Acrylic polymer-B, Acrylic resin, Methyl acetate, Methyl amyl ketone, Polyester resin-B, Substituted benzotriazole GAL WT: 8.84 WT PCT SOLIDS: 40.19 VOL PCT SOLIDS: 37.94 SOLVENT DENSITY: 8.52 VOC LE: 2.8 VOC AP: 1.8 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8840S™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-B, Acrylic resin, Butyl acetate, Dimethyl glutarate, Isopropyl alcohol, Methyl amyl ketone, Polyester resin-A GAL WT: 8.03 WT PCT SOLIDS: 51.70 VOL PCT SOLIDS: 44.32 SOLVENT DENSITY: 6.97 VOC LE: 3.7 VOC AP: 3.5 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8900E™ Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-B, Butyl acetate, Isopropyl alcohol, Methyl amyl ketone, Polyester resin-B, Synthetic resin-A GAL WT: 8.15 WT PCT SOLIDS: 55.81 VOL PCT SOLIDS: 47.18 SOLVENT DENSITY: 6.84 VOC LE: 3.5 VOC AP: 3.3 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

8989S™ 2,4-pentanedione, Dibutyl tin dilaurate GAL WT: 8.16 WT PCT SOLIDS: 5.00 VOL PCT SOLIDS: 4.68 SOLVENT DENSITY: 8.14 VOC LE: 7.8 VOC AP: 7.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

N0001EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Butyl acetate, Carbon black(1.6%), Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Methyl ethyl ketone, Polyester resin-A GAL WT: 8.19 WT PCT SOLIDS: 53.63 VOL PCT SOLIDS: 46.43 SOLVENT DENSITY: 7.10 VOC LE: 3.5 VOC AP: 3.2 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

N0001EZ™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-B, Butyl acetate, Carbon black(1.0%), Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Methyl ethyl ketone, Polyester resin-A GAL WT: 8.18 WT PCT SOLIDS: 53.85 VOL PCT SOLIDS: 46.89 SOLVENT DENSITY: 7.11 VOC LE: 3.5 VOC AP: 3.2 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

N0006EX™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-C, Acrylic resin, Aluminum hydroxide, Amorphous silica-A, Butyl acetate, Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Methyl isoamyl ketone, Polyester resin-A, Titanium dioxide(26.6%) GAL WT: 10.19 WT PCT SOLIDS: 61.55 VOL PCT SOLIDS: 44.54 SOLVENT DENSITY: 7.05 VOC LE: 3.5 VOC AP: 3.0 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

N0006EZ™ 2-ethylhexyl acetate, Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-A, Aromatic hydrocarbon-B, Butyl acetate, Ethyl acetate, Isopropyl alcohol, Methyl amyl ketone, Polyester resin-A, Titanium dioxide(21.2%) GAL WT: 9.70 WT PCT SOLIDS: 59.84 VOL PCT SOLIDS: 45.15 SOLVENT DENSITY: 7.09 VOC LE: 3.5 VOC AP: 3.0 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

PT101™ Acrylic polymer-A, Acrylic resin, Aluminum hydroxide, Amorphous silica-A, Butyl acetate, Titanium dioxide(58.3%) GAL WT: 15.47 WT PCT SOLIDS: 77.09 VOL PCT SOLIDS: 51.74 SOLVENT DENSITY: 7.30 VOC LE: 3.5 VOC AP: 3.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

PT1015™ Acrylic polymer-A, Acrylic resin, Amorphous silica-B, Butyl acetate, Ethyl acetate, Heptane, Isopropyl alcohol, Methyl amyl ketone, Mica, Polyester resin-D, Titanium dioxide(3.8%) GAL WT: 8.64 WT PCT SOLIDS: 57.08 VOL PCT SOLIDS: 46.98 SOLVENT DENSITY: 6.98 VOC LE: 3.7 VOC AP: 3.7 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

PT105™ Acrylic polymer-A, Butyl acetate, Carbon black(4.5%), Methyl amyl ketone, Methyl ethyl ketone, Primary amyl acetate **GAL WT: 8.40 WT PCT SOLIDS: 56.07 VOL PCT SOLIDS: 48.64 SOLVENT DENSITY: 7.16 VOC LE: 3.7 VOC AP: 3.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT1051™ 2-methyl butyl acetate, Acrylic polymer-A, Amorphous silica-A, Butyl acetate, Calcium sodium borosilicate, Hydrotreated heavy naphtha (petroleum)-A, Hydrotreated heavy naphtha (petroleum)-B, Kerosine (petroleum), hydrodesulfurized, Methyl amyl ketone, Primary amyl acetate, Silver(6%*) **GAL WT: 9.27 WT PCT SOLIDS: 55.39 VOL PCT SOLIDS: 40.22 SOLVENT DENSITY: 6.89 VOC LE: 4.1 VOC AP: 4.1 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

PT107™ Acrylic polymer-A, Butyl acetate, Carbon black(0.5%), Methyl amyl ketone **GAL WT: 8.24 WT PCT SOLIDS: 56.51 VOL PCT SOLIDS: 49.26 SOLVENT DENSITY: 7.06 VOC LE: 3.6 VOC AP: 3.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT110™ 1,2,4-trimethyl benzene(2%*), 2-methyl butyl acetate, Acrylic polymer-A, Aluminum(22%*), Aromatic hydrocarbon-B, Butyl acetate, Hydrotreated heavy naphtha (petroleum)-A, Hydrotreated heavy naphtha (petroleum)-B, Methyl amyl ketone, Primary amyl acetate, Tetraethyl orthosilicate **GAL WT: 8.81 WT PCT SOLIDS: 49.37 VOL PCT SOLIDS: 34.29 SOLVENT DENSITY: 6.83 VOC LE: 4.5 VOC AP: 4.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

PT112™ 1,2,4-trimethyl benzene(2%*), 2-methyl butyl acetate, Acrylic polymer-A, Aluminum(26%*), Aromatic hydrocarbon-B, Butyl acetate, Cumene(0.1%*@), Hydrotreated heavy naphtha (petroleum)-A, Hydrotreated heavy naphtha (petroleum)-B, Methyl amyl ketone, Primary amyl acetate, Stoddard solvent **GAL WT: 9.10 WT PCT SOLIDS: 53.24 VOL PCT SOLIDS: 38.24 SOLVENT DENSITY: 6.87 VOC LE: 4.3 VOC AP: 4.3 FLASH POINT: 100 °F - 141 °F H: 2 F: 2 R: 1 OSHA STORAGE: II TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

PT114™ 1,2,4-trimethyl benzene(1%*), 2-methyl butyl acetate, Acrylic polymer-A, Aluminum(26%*), Aromatic hydrocarbon-B, Butyl acetate, Hydrotreated heavy naphtha (petroleum)-A, Hydrotreated heavy naphtha (petroleum)-B, Methyl amyl ketone, Primary amyl acetate **GAL WT: 9.10 WT PCT SOLIDS: 53.24 VOL PCT SOLIDS: 40.80 SOLVENT DENSITY: 6.80 VOC LE: 4.3 VOC AP: 4.3 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 2 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

PT116™ 2-methyl butyl acetate, Acrylic polymer-A, Aluminum(23%*), Aromatic hydrocarbon-B, Butyl acetate, Hydrotreated heavy naphtha (petroleum)-A, Hydrotreated heavy naphtha (petroleum)-B, Methyl amyl ketone, Primary amyl acetate, Stoddard solvent **GAL WT: 9.01 WT PCT SOLIDS: 53.23 VOL PCT SOLIDS: 39.00 SOLVENT DENSITY: 6.86 VOC LE: 4.2 VOC AP: 4.2 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 1 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES**

PT120™ Acrylic polymer-A, Butyl acetate, Carbazole violet pigment, Methyl amyl ketone **GAL WT: 8.32 WT PCT SOLIDS: 54.22 VOL PCT SOLIDS: 47.05 SOLVENT DENSITY: 7.20 VOC LE: 3.8 VOC AP: 3.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT122™ Acrylic polymer-A, Additive, Butyl acetate, C.i. pigment blue 60, Methyl amyl ketone **GAL WT: 8.49 WT PCT SOLIDS: 56.82 VOL PCT SOLIDS: 49.18 SOLVENT DENSITY: 7.23 VOC LE: 3.7 VOC AP: 3.7 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT124™ Acrylic polymer-A, Butyl acetate, Methyl amyl ketone, Phthalocyanine blue pigment-A, Phthalocyanine blue pigment-B, Primary amyl acetate **GAL WT: 8.64 WT PCT SOLIDS: 54.54 VOL PCT SOLIDS: 46.20 SOLVENT DENSITY: 7.37 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT125™ Acrylic polymer-A, Butyl acetate, Methyl amyl ketone **GAL WT: 8.20 WT PCT SOLIDS: 54.15 VOL PCT SOLIDS: 46.92 SOLVENT DENSITY: 7.09 VOC LE: 3.8 VOC AP: 3.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT127™ 2-methyl butyl acetate, Acrylic polymer-A, Butyl acetate, Methyl amyl ketone, Phthalocyanine blue pigment-A, Primary amyl acetate, Proprietary copper compound(2%*) **GAL WT: 8.85 WT PCT SOLIDS: 59.18 VOL PCT SOLIDS: 50.50 SOLVENT DENSITY: 7.39 VOC LE: 3.6 VOC AP: 3.6 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT132™ Acrylic polymer-A, Butyl acetate, Methyl amyl ketone, Phthalocyanine green, Primary amyl acetate **GAL WT: 8.63 WT PCT SOLIDS: 52.06 VOL PCT SOLIDS: 43.27 SOLVENT DENSITY: 7.31 VOC LE: 4.1 VOC AP: 4.1 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT133™ Acrylic polymer-A, Butyl acetate, Methyl amyl ketone **GAL WT: 8.21 WT PCT SOLIDS: 54.18 VOL PCT SOLIDS: 46.90 SOLVENT DENSITY: 7.09 VOC LE: 3.8 VOC AP: 3.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT140™ Acrylic polymer-A, Aluminum salt, Bismuth vanadium oxide(43%*), Butyl acetate, Methyl amyl ketone, Molybdate/calcium, Primary amyl acetate, Titanium dioxide(1.2%), Yellow bismuth vanadate pigment(5%*), Zinc phosphate(3%*) **GAL WT: 14.72 WT PCT SOLIDS: 74.80 VOL PCT SOLIDS: 48.58 SOLVENT DENSITY: 7.18 VOC LE: 3.7 VOC AP: 3.7 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT144™ Acrylic polymer-A, Butyl acetate, C.i. pigment yellow 154, Methyl amyl ketone, Primary amyl acetate, T-butyl acetate, Titanium dioxide(1.4%) **GAL WT: 9.17 WT PCT SOLIDS: 60.16 VOL PCT SOLIDS: 49.02 SOLVENT DENSITY: 7.15 VOC LE: 3.7 VOC AP: 3.7 VOC LE (TBAC): 3.6 VOC AP (TBAC): 3.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT148™ 2-methyl butyl acetate, Acrylic polymer-A, Butyl acetate, Isoindolinone pigment, Methyl amyl ketone, Primary amyl acetate **GAL WT: 9.13 WT PCT SOLIDS: 63.30 VOL PCT SOLIDS: 53.19 SOLVENT DENSITY: 7.13 VOC LE: 3.3 VOC AP: 3.3 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC**

TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

PT154™ 2-methyl butyl acetate, Acrylic polymer-A, Butyl acetate, Methyl amyl ketone, Monoazo pigment, Primary amyl acetate **GAL WT: 9.46 WT PCT SOLIDS: 64.60 VOL PCT SOLIDS: 54.47 SOLVENT DENSITY: 7.31 VOC LE: 3.4 VOC AP: 3.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT162™ Acrylic polymer-A, Butyl acetate, C.i. pigment red 254, Methyl amyl ketone, Methyl ethyl ketone, Pigment red 202, T-butyl acetate **GAL WT: 8.50 WT PCT SOLIDS: 53.76 VOL PCT SOLIDS: 45.83 SOLVENT DENSITY: 7.24 VOC LE: 3.9 VOC AP: 3.9 VOC LE (TBAC): 3.9 VOC AP (TBAC): 3.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT164™ Acrylic polymer-A, Butyl acetate, Kaolin, Methyl amyl ketone, Methyl ethyl ketone, Pigment red 202, Quinacridone pigment **GAL WT: 8.66 WT PCT SOLIDS: 56.97 VOL PCT SOLIDS: 48.13 SOLVENT DENSITY: 7.23 VOC LE: 3.7 VOC AP: 3.7 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT165™ Acrylic polymer-A, Butyl acetate, C.i. pigment red 254, Isopropyl alcohol, Methyl amyl ketone, T-butyl acetate, Titanium dioxide(0.8%) **GAL WT: 9.06 WT PCT SOLIDS: 62.14 VOL PCT SOLIDS: 51.81 SOLVENT DENSITY: 7.13 VOC LE: 3.4 VOC AP: 3.4 VOC LE (TBAC): 3.3 VOC AP (TBAC): 3.3 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT166™ Acrylic polymer-A, Butyl acetate, Methyl amyl ketone, Methyl ethyl ketone, Quinacridone pigment **GAL WT: 8.73 WT PCT SOLIDS: 60.44 VOL PCT SOLIDS: 52.07 SOLVENT DENSITY: 7.21 VOC LE: 3.5 VOC AP: 3.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT167™ Acrylic polymer-A, Butyl acetate, Methyl amyl ketone, Methyl ethyl ketone, Organic amide, Quinacridone pigment **GAL WT: 8.65 WT PCT SOLIDS: 55.83 VOL PCT SOLIDS: 46.94 SOLVENT DENSITY: 7.21 VOC LE: 3.8 VOC AP: 3.8 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT168™ 2-methyl butyl acetate, Acrylic polymer-A, Acrylic resin, Barium sulfate, Butyl acetate, Methyl amyl ketone, Perylene maroon, Primary amyl acetate **GAL WT: 8.87 WT PCT SOLIDS: 60.79 VOL PCT SOLIDS: 51.76 SOLVENT DENSITY: 7.39 VOC LE: 3.5 VOC AP: 3.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT169™ Acrylic polymer-A, Barium sulfate, Butyl acetate, Methyl amyl ketone, Methyl ethyl ketone, Perylene maroon **GAL WT: 8.89 WT PCT SOLIDS: 60.71 VOL PCT SOLIDS: 51.13 SOLVENT DENSITY: 7.15 VOC LE: 3.5 VOC AP: 3.5 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT181™ Acrylic polymer-A, Butyl acetate, Iron hydroxide, Methyl amyl ketone **GAL WT: 12.49 WT PCT SOLIDS: 72.78 VOL PCT SOLIDS: 53.30 SOLVENT DENSITY: 7.27 VOC LE: 3.4 VOC AP: 3.4 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT183™ 2-methyl butyl acetate, Acrylic polymer-A, Butyl acetate, Light yellow lemon yellow oxide pigment, Methyl amyl ketone, Primary amyl acetate, Wetting agents for solvent borne coatings **GAL WT: 9.66 WT PCT SOLIDS: 57.19 VOL PCT SOLIDS: 41.30 SOLVENT DENSITY: 7.02 VOC LE: 4.1 VOC AP: 4.1 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT185™ Acrylic polymer-A, Barium sulfate, Butyl acetate, Iron oxide, Methyl amyl ketone, Monoazo pigment, T-butyl acetate, Titanium dioxide(1.0%) **GAL WT: 13.25 WT PCT SOLIDS: 74.20 VOL PCT SOLIDS: 52.90 SOLVENT DENSITY: 7.25 VOC LE: 3.4 VOC AP: 3.4 VOC LE (TBAC): 3.3 VOC AP (TBAC): 3.3 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT187™ 2-methyl butyl acetate, Acrylic polymer-A, Butyl acetate, Iron oxide, Methyl amyl ketone, Primary amyl acetate, Wetting agents for solvent borne coatings **GAL WT: 9.42 WT PCT SOLIDS: 58.97 VOL PCT SOLIDS: 45.12 SOLVENT DENSITY: 7.09 VOC LE: 3.9 VOC AP: 3.9 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT190™ Bis(1,2,2,6,6-pentamethyl-4-piperidinyl) sebacate, Decanedioic acid, methyl 1,2,2,6,6-pentamethyl-4-piperidinyl ester, Ethyl 3-ethoxy propionate, Ethyl acetate, Methyl ethyl ketone, Poly(oxy-1,2-ethanediyl),.alpha.-[3-[3-(2h-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy phenyl], Polyethylene glycol, Triethylenediamine, Ultraviolet absorber **GAL WT: 8.08 WT PCT SOLIDS: 52.40 VOL PCT SOLIDS: 46.95 SOLVENT DENSITY: 7.28 VOC LE: 3.8 VOC AP: 3.8 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT191™ Acetic acid, Ethyl acetate, Ethylbenzene(1.8%*@), Xylene(7%*@) **GAL WT: 7.53 WT PCT SOLIDS: 0.98 VOL PCT SOLIDS: 0.66 SOLVENT DENSITY: 7.50 VOC LE: 7.5 VOC AP: 7.5 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT192™ Bis(1,2,2,6,6-pentamethyl-4-piperidinyl) sebacate, Decanedioic acid, methyl 1,2,2,6,6-pentamethyl-4-piperidinyl ester, Ethyl 3-ethoxy propionate, Ethylbenzene(0.2%*@), Methyl ethyl ketone, Poly(oxy-1,2-ethanediyl),.alpha.-[3-[3-(2h-benzotriazol-2-yl)-5-(1,1-dimethylethyl)-4-hydroxy phenyl], Polyethylene glycol, Triethylenediamine, Ultraviolet absorber **GAL WT: 7.97 WT PCT SOLIDS: 55.76 VOL PCT SOLIDS: 49.31 SOLVENT DENSITY: 6.96 VOC LE: 3.5 VOC AP: 3.5 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT195™ Bis(1,2,2,6,6-pentamethyl-4-piperidinyl) sebacate, Decanedioic acid, methyl 1,2,2,6,6-pentamethyl-4-piperidinyl ester, Ethyl 3-ethoxy propionate, Ethyl acetate, Methyl ethyl ketone, Triethylenediamine **GAL WT: 7.45 WT PCT SOLIDS: 27.40 VOL PCT SOLIDS: 24.25 SOLVENT DENSITY: 7.14 VOC LE: 5.4 VOC AP: 5.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO**

PT196™ Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-A, Amorphous silica-B, Amorphous silica - silica base, Butyl acetate, Ethyl acetate, Isopropyl alcohol, Limestone (calcium carbonate), Methyl amyl ketone, Polyester resin-D, Primary amyl acetate **GAL WT: 8.82 WT PCT SOLIDS: 49.02 VOL PCT SOLIDS: 34.23**

**SOLVENT DENSITY: 6.90 VOC LE: 3.8 VOC AP: 2.9 FLASH POINT: Below 20 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance
PHOTOCHEMICALLY REACTIVE: NO**

PT197™ Acetic acid, Acetone, Acrylic polymer-B, Butyl acetate, Ethylbenzene(0.5%*®), Methyl amyl ketone, Polyester resin-B, Xylene(2%*®) GAL WT: 8.26 WT PCT SOLIDS: 66.06 VOL PCT SOLIDS: 59.04 SOLVENT DENSITY: 6.86 VOC LE: 2.4 VOC AP: 2.1 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

PT198™ Acrylic polymer-A, Ethyl acetate, Heptane, Methyl amyl ketone, Polyester resin-D GAL WT: 8.45 WT PCT SOLIDS: 71.86 VOL PCT SOLIDS: 65.82 SOLVENT DENSITY: 6.91 VOC LE: 2.4 VOC AP: 2.4 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

PT199™ 1,2,4-trimethyl benzene(1%*), Aromatic hydrocarbon-B, Ethyl acetate, Heptane, Polyester resin-D GAL WT: 8.87 WT PCT SOLIDS: 80.77 VOL PCT SOLIDS: 77.36 SOLVENT DENSITY: 7.31 VOC LE: 1.7 VOC AP: 1.7 FLASH POINT: 20 °F to below 73 °F H: 1 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: YES

PT290™ Acetone, Acrylic polymer-A, Acrylic resin, Amorphous silica-B, Butyl acetate, Isopropyl alcohol, Methyl amyl ketone GAL WT: 8.04 WT PCT SOLIDS: 47.37 VOL PCT SOLIDS: 38.98 SOLVENT DENSITY: 6.93 VOC LE: 4.2 VOC AP: 4.0 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

PT291™ Acetone, Acrylic polymer-A, Butyl acetate, Propylene glycol monomethyl ether acetate GAL WT: 8.28 WT PCT SOLIDS: 56.61 VOL PCT SOLIDS: 50.69 SOLVENT DENSITY: 7.28 VOC LE: 3.2 VOC AP: 2.9 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

RKP19478™ Acrylic polymer-B, Amorphous silica-A, Butyl acetate, Dimethyl glutarate, Ethylene glycol monobutyl ether acetate(2%*®), Methyl amyl ketone, Methyl ethyl ketone, Toluene(3%*®) GAL WT: 9.06 WT PCT SOLIDS: 59.71 VOL PCT SOLIDS: 48.28 SOLVENT DENSITY: 7.09 VOC LE: 3.6 VOC AP: 3.6 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 0 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

TP32907™ Ethyl 3-ethoxy propionate, Ethyl acetate, Heptane, Methyl amyl ketone GAL WT: 7.15 WT PCT SOLIDS: 0.00 VOL PCT SOLIDS: 0.00 SOLVENT DENSITY: 7.15 VOC LE: 7.2 VOC AP: 7.2 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

VGF70050™ Acrylic polymer-B, Ethyl 3-ethoxy propionate, Methyl amyl ketone GAL WT: 8.26 WT PCT SOLIDS: 57.62 VOL PCT SOLIDS: 51.03 SOLVENT DENSITY: 7.17 VOC LE: 3.5 VOC AP: 3.5 FLASH POINT: 20 °F to below 73 °F H: 2 F: 3 R: 1 OSHA STORAGE: IB TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

VGP28269™ Butyl acetate, Dibutyl tin dilaurate, Methyl amyl ketone GAL WT: 7.06 WT PCT SOLIDS: 1.15 VOL PCT SOLIDS: 0.93 SOLVENT DENSITY: 7.05 VOC LE: 7.0 VOC AP: 7.0 FLASH POINT: 73 °F to below 100 °F H: 2 F: 3 R: 0 OSHA STORAGE: IC TSCA STATUS: In Compliance PHOTOCHEMICALLY REACTIVE: NO

Footnotes:

TSCA: in compliance In compliance with TSCA Inventory requirements for commercial purposes.

ACGIH American Conference of Governmental Industrial Hygienists.

IARC International Agency for Research on Cancer.

NTP National Toxicology Program.

OSHA Occupational Safety and Health Administration.

PNOR Particles not otherwise regulated.

PNOC Particles not otherwise classified.

STEL Short term exposure limit.

TWA Time-weighted average.

* VOC less exempt (theoretical) and VOC as packaged (theoretical) are based upon the VOC of the packaged material at the point of manufacture.

TBAC is not universally recognized as an exempt solvent.

Users should consult the applicable regulations for their region.

All products denoted with TM or R are trademarks or registered trademarks of Axalta Coating Systems, LLC and all affiliates.

* = Section 313 Supplier Notification: These chemicals are subject to the reporting requirements of Section 313 of the Emergency planning and Right-to-Know act of 1986 and of 40 CFR 372.

@ = Listed as a Clean Air Act Hazardous Air Pollutant.

= EPCRA Section 302 - Extremely hazardous substances.

Notice:

The information on this Material Safety Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process.

Product Manager: Refinish Sales

Prepared by: Y. B. Yarbrough